CHEMATEX DYES & CHEMICALS

嘉玛富 C

CHEMAFLUID C

高份子聚合物染浴防绉剂，能防止任何纤维在湿处理时形成折绉印。

物理性质

外观	：	透明清澈液体。
酸碱值（1% 溶液）	：	近乎中性。
成份	：	高份子有基聚合物。
离子性	：	非离子性。
溶解性	：	容易溶于水。
兼容性	：	与阴离子和阳离子物质完全兼容。
储存稳定性	：	在 20°C，密封容器中，能保持稳定达一年以上。

应用范围

- **CHEMFLUID C** 能降低织物与织物之间的磨擦系数，从而防止在湿处理过程当中（例如：煮炼、染色、皂煮…等），永久性折绉痕的形成。绳状染色，织物更加张开及滑行，最终能改善匀染性。
- **CHEMFLUID C** 能降低织物与机械金属之间的磨擦系数，从而提高织物的运行性，避免因织物与金属磨擦而形成损伤及折痕，同时减低织物表面毛球的产生。
- **CHEMFLUID C** 特别针对保护簿身织物在湿处理时形成绉痕和折痕。
- **CHEMFLUID C** 对纤维和染料并没有亲和能力，所以对染料得色量并无不良影响。
- **CHEMFLUID C** 对染色后牢度没有影响。
- **CHEMFLUID C** 对织物手感并无影响。
- **CHEMFLUID C** 能耐高温、耐酸、耐碱及对硬水不敏感。
- 由于 **CHEMFLUID C** 不会起泡，适合于喷射染色机上使用。

应用建议

为求 **CHEMFLUID C** 能发挥最佳性能，一般建议先把 **CHEMFLUID C** 加进机械运行，然后再把织物加进机械。

CHEMFLUID C 可以先用温水稀释搅拌，然后加入整理浴液当中。

CHEMFLUID C 的使用量是因应织物形成绉痕的容易性、机械种类及机械负荷量而定。

一般使用量建议如下：

针织物、布匹	-	**CHEMFLUID C**	1 - 2 克/升
紧密织物，如扁机领	-	**CHEMFLUID C**	2 - 3 克/升

… 完 …

本数据是基于精密试验所得，以供阁下参考。对于使用后所得之一切结果，不负任何责任。这是因染厂有许多的变量超出我们所能控制之范围。本公司仅保证产品之质量稳定不变。

The information and data in this bulletin are based on accurate laboratory researches and are intended for your guidance. We cannot, however, accept any responsibility for the results obtained, in view of the numerous factors of application are beyond our control. Our guarantee is limited to the unvarying quality of our products.