



Chematex Dyes & Chemicals

CHEMALON YELLOW S-6G

嘉玛隆 黄 S-6G

| 标准深度 | 酸碱值范围 | 日晒牢度 | 升华牢度 | 洗水牢度 | 干摩擦牢度 |
|----------------|----------|----------------|----------------------|------------------|-------------|
| Standard Depth | pH Range | Light Fastness | Sublimation Fastness | Washing Fastness | Dry Rubbing |
| 0.90 | 3-7 | 6 | 4-5 | 5 | 5 |

缩写简介(Abbreviations):

| | | | | | |
|----|---|------------------------|---|---|-----------------------|
| B | = | 偏蓝 Bluer | Y | = | 偏黄 Yellower |
| R | = | 偏红 Redder | G | = | 偏绿 Greener |
| D | = | 偏沉 Duller | | | |
| Br | = | 偏鲜 Brilliance | | | |
| C | = | 棉沾染 Stain on cotton | E | = | 色变 Color Change |
| N | = | 尼龙沾染 Stain on nylon | W | = | 羊毛沾染 Stain on wool |

牢度特性: (Testing Methods)

| | |
|------------------------------|--|
| 日光: (Light Fastness Test) | ISO105-B02, 氙弧灯 (Xenon Arc Lamp) |
| 升华: (Sublimation Test) | 180°C X 30 秒 (色变性及对涤纶的污染) (Color change and stain on polyester) |
| 还原洗后的水洗: (Washing Test) | AATCC IIA |
| 还原洗后的摩擦: (Rubbing Test) | ISO105-X12 |