



TECHNICAL INFORMATION

ZHONGSHAN DIC COLOUR CO.,LTD.

TECHNICAL SERVICE LABORATORY

RYUDYE-W ASSISTER ST 柔软剂

[产品说明]

改善印花浆的柔软度,添加少量该产品可以提高印花面的柔软度,

[保存期]

室温贮藏一年。避免贮存于摄氏40度以上或摄氏低温0度以下。

[环保标准]

1. 符合日本厚生省对“福尔马林(甲醛)”所定之安全标准(昭和49-34)号指令;
2. 符合欧盟对“烷基酚聚氧乙烯醚(APE0)”所定之安全标准(2003/53/EC)号指令;
3. 符合欧盟对“邻苯二甲酸盐(PHTHALATE)”所定之安全标准(2005/84/EC)号指令;
4. 符合欧盟禁用有害偶氮染料(AZO)含量不超过30mg/kg(2002/61/EC)号指令;
5. 符合欧盟EN71 PART 3对重金属含量的标准;
6. 不含PVC(测试方法:FTIR);
7. 符合REACH 法规规定的高度关注物质SVHC(2010版)。

[注意事项]

1. 实际使用中,本品的一般添加量为2-3%(重量比),建议最大添加量不要超过5%(重量比),添加后的印花浆料应该充分搅拌均匀。
2. 添加太多的RYUDYE-W ASSISTER ST,会降低印花面的摩擦牢度;具体的添加量,希望用户做进一步实验确认。

以上资料,仅供客户参考,希望客户经试验后能善加利用。

Item mentioned in this information are for customers references and limited to certain examples although they are based on the most reliable data obtained by our company. It is hoped that customers make the best use of these produces after careful examination.

中山 DIC 色料有限公司

ZHONGSHAN DIC COLOUR CO., LTD.

中国广东省中山市坦洲镇第二工业区(PC: 528467)

2nd Industrial Zone, Tanzhou, Zhongshan City, Guangdong, China

Tel: +86(760)8665-5822

Fax: +86(760)86655824