


特性 Properties


溶解度 Solubility	90°C	40G/L
	90°C→25°C	30G/L
顏色濃度 Color consistency	鎢絲燈 Tungsten Lamp	較紅味,較亮 redder,somewhat brighter
	TL84 白日光燈 TL 84 Lamp	較黃味,較亮 yellower,somewhat brighter
金屬離子的影響 Effect of metal In dyebath	鐵 Iron	4-5
	銅 Copper	1
	鉻 Chrome	1
半尼龍混紡之污染性 Staining on half nylon blends	醋酸纖維 Acetate	4-5
	棉 Cotton	3
	聚酯 Polyester	4
	壓克力 Acrylic	5
拔染性 Dischargeability	氯化亞錫 Stannous chloride	2
	Decrolin	2
剝色性 Decolouration	1	

試驗項目 Test item		固色前 Before fixing			固色後 After fixing		
		N	PA	Co	N	PA	Co
水洗堅牢度 Washing	AATCC 2A	4-5	4-5	4-5	5	5	5
	ISO 105-C02	3-4	4-5	4-5	5	5	5
	ISO 105-C03	3	4	4-5	4-5	5	5
	ISO C06-B2S	4	4-5	5	5	5	5
	ISO C06-C2S	3	4	4	5	3-4	4-5
耐水堅牢度 Water	ISO-E01	5	4	4-5	5	5	5
耐海水堅牢度 Sea water	ISO-E02	5	4-5	4-5	5	5	4-5
耐汗堅牢度 Perspiration ISO-E04	酸 acid	5	4	4-5	5	5	5
	鹼 alkaline	5	3	3-4	5	5	5
耐氯水堅牢度 Chlorinated water ISO-E03	20 ppm	4			4		
	100ppm	1			1-2		
磨擦堅牢度 Rubbing ISO-X12	乾 Dry	5			5		
	溼 Wet	5			5		
熱壓堅牢度 Hot pressing ISO-X11	立即 Immed.	3					
	4 小時後 After 4hr	5					
日光堅牢度 Light	ISO-B02	0.1% o.w.f	0.5% o.w.f	1% o.w.f.	2% o.w.f.		
		2-3	3	3-4	4		


以 MESITOL NBS 2% 固色後 (After fixed with MESITOL NBS 2%)




0.1%



0.5%



1.0%




2.0%


# Everacid Orange N-G

( C.I. Acid-Orange 56)

昇溫上色曲線  
Step dyeing



PH 依存性  
Dependency on pH



- ◇ 明亮的橘色  
Brilliant orange
- ◇ 高色值  
High color value
- ◇ 極佳溼潤堅牢度  
Very good wetting fastness
- ◇ 注意日光堅牢度  
Pay attention to lightfastness

## 染色特性 Dyeing properties

瞬染性 Strike	小 small
移染性 Migration	佳 good
橫條遮蓋性 Coverage of barre	佳 good
尼龍和羊毛相對染料分配性 Relative dye distribution between polyamide and wool fiber	尼龍=羊毛 PA=Wool
羊毛的色光與尼龍比較 Shade on wool as compared with polyamide	微鈍 trace duller