



Dyeing Properties 特性

Characteristics		Evaluation
Reactivity 反應性		II
Substantivity 親和性		B
Migration 移染性		3-4
Washing off 洗淨性		3-4
Solubility g/l 溶解度	50°C Water	100
	50°C Water+50 g/l Salt	100
High temp. Dyeing 高溫染色性	Dyed fabric 色布	4-5
	Dye Liquor 染浴	4-5
Color constancy 色恆性	Tungsten Lamp	Y
	TL 84 Lamp	Y
Metallic ions 金屬離子	Fe ⁺⁺ 鐵	4-5
	Cu ⁺⁺ 銅	1
Resin finishing 樹脂加工	Melamine 三聚氰胺	3-4
	Glyoxal 乙二醛	3-4
Shade change after fixing treatment 固色後變色性	Polyamide 聚乙醯胺	4-5
	Quaternary ammonium salt 四級胺鹽	4
Stripping 脫色性	(1)	1-2
	(2)	1-2
	(3)	1
	(4)	3-4
Discharge ability 拔染性	Neutral 中性	2-3
	Alkaline 鹼性	3


吸盡固著曲線 Exhaustion & Fixation



溫度依存性 Dependency on temperature



芒硝依存性 Dependency on Glauber's salt



Everzol Red ED-7B




Fastness before fixing treatment 固色前牢度表

Evaluation		Depth of shade 染色濃度	Color change 變褪色	Staining 污染						Evaluation		Depth of shade 染色濃度	Grade 級數	
				Acetate 醋酸纖維	Cotton 棉	Nylon 尼龍	Polyester 聚酯	Acrylic 壓克力	Wool 羊毛					
Washing 耐水洗	ISO C02	1.0%	4-5	5	4-5	5	5	5	5	5	Chlorinated Water耐氯水(20ppm)	1.0%	1	
	ISO C03		4-5	5	4	5	5	5	5	Peroxide Bleaching雙氧水漂白	1.0%	4-5		
	ISO C04		4-5	5	3	5	5	5	3-4	Rubbing 耐摩擦	Dry 乾	1.0%	4-5	
	ISO C06-C1S		4-5	5	4	5	5	5	5		Wet 濕	1.0%	4-5	
	ISO C06-C2S		4-5	5	5	5	5	5	5	M&S C9A 擬溼日光 (detergent Light)	0.1%	4-5		
	M&S C4A		4-5	5	5	5	5	5	5		1.0%	4-5		
Water 耐水		1.0%	5	5	5	5	5	5	5	M&S C10A (UK-TO)	1.0%	4		
Hot Water 耐熱水		1.0%	5	5	5	5	5	5	5	Saliva (DIN) 耐唾液	1.0%	5		
Sea Water 耐海水		1.0%	5	5	5	5	5	5	5	Hot- Pressing 耐熱壓	Dry 乾	Immediately	1.0%	3-4
Post mercerizing 後絲光		1.0%	4B		2-3						4 Hours after	1.0%	4	
Acid hydrolysis 酸水解		1.0%	5	5	5	5	5	5	5	Wet 濕	Immediately	1.0%	3-4	
Perspiration 耐汗	Acid 酸	1.0%	5	5	5	5	5	5	5		4 Hours after	1.0%	4	
	Alkali 鹼		5	5	5	5	5	5	5	Dry cleaning 耐乾洗	3.0%	*		

Light Fastness 日光堅牢度

Evaluation		Dyeing Depth 染色濃度	Color Change 20 AFU	Grade ISO Blue Scale	Evaluation		Dyeing Depth 染色濃度	Color Change 20 AFU	Grade ISO Blue Scale
Artificial Light (Xenon-Arc Lamp) 耐日光		0.1 %	2-3	4	Perspiration Light 耐汗日光	Acid Alkali	1.0 %	4-5	5-6
		0.3 %	3	4-5				3	5
		1.0 %	3-4	5					
		3.0 %	4	5-6					
		6.0 %	4-5	6					

浴比依存性 Dependency on Liquor ratio



鹼依存性 Dependency on alkali

