
TECHNICAL INFORMATION

Dexcel[®] Clear 288P**High-Fastness Soft Instant Binder****[Main Application]**

High-Fastness Soft Instant Binder for pigment printing on cotton fabrics, also can be used for a part of Nylon, polyester, polyester and cotton blended. Excellent permeability, bright color, is suitable for hand and machine printing.

[Storage Stability]

Stored in a cool and dry place for one year, recommend to store at temperature between 0~40°C.

[Environmental Criteria]

1. Fulfill Formaldehyde criteria of Japan Law 112 (Showa 49-34);
2. Fulfill APEO criteria of EU Directive (2003/53/EC);
3. Fulfill Phthalate criteria of EU Directive (2005/84/EC);
4. Fulfill Heavy Metal Criteria of EN-71 Part3:1994;
5. Not detected PVC (Test Method: FTIR);
6. Fulfill AZO criteria (not exceed 20mg/kg) of China Directive (GB18401-2010);
7. Fulfill SVHC (2014 Edition) of EU Reach.

[Typical Formulation]

	Low	Medium	High
Ryudye [®] -W Colors	1	5	10
Dexcel [®] Clear 288P	98-97	94-92	91-89
Ryudye [®] -W Fixer J-52	1-2	1-3	1-3
Total (Weight %)	100	100	100

[Printing Process]

Printing → Pre-drying (70-100 °C, 1-2Mins) → Heat Treatment (130-150 °C, 2-3Mins)

[Fastness Test]

1. Washing fastness test (60 °C×1Hr × 4times) : 4.0 - 5.0 Grade
2. Rubbing fastness test (JIS L-0849, 100Rounds / 3Mins) : 3.0 - 4.0 Grade

Note: Fastness Grade from 1.0 to 5.0, Grade 5.0 is the best.

[Matters Needing Attention]

1. In order to ensure excellent fastness, we advise adding the right amount of Ryudye[®]-W Fixer J-52 (Long-time limiting, 24Hrs);
2. Recommended screen mesh from 800 to 1500;
3. In order to prevent drying too quickly and cause block up the screen when the humidity is too low (e.g. Autumn or Winter), you can add 1-3% wetting agent (Ryudye[®]-W Assister 502);
4. All matters in this instructions is obtained based on the standard test method, so in order to avoid any difference, the user must test according to their own use method and requirements before the product used for production.