

Ryudye®-W KN White EFW-T White Rubber Binder for Hand Printing Ryudye®-W KN Clear EFC-T Clear Rubber Binder for Hand Printing

[Main Application]

Environmental rubber binder, is suitable for hand printing on cotton or T/C knitted fabrics. Excellent processability, soft handle, high whiteness, covering power and high elasticity. The products can fulfill the baby formaldehyde criteria of Japan Law 112 (Showa 49-34).

[Storage Stability]

Stored in a cool and dry place for one year, recommend to store at temperature between 0~40°C.

[Environmental Criteria]

- 1. Fulfill Formaldehyde criteria of Japan Law 112 (Showa 49-34);
- 2. Fulfill APEO criteria of EU Directive (2003/53/EC);
- 3. Fulfill Phthalate criteria of EU Directive (2005/84/EC);
- 4. Fulfill Heavy Metal Criteria of EN-71 Part3:1994;
- 5. Not detected PVC (Test Method: FTIR);
- 6. Fulfill AZO criteria (not exceed 20mg/kg) of China Directive (GB18401-2010);
- 7. Fulfill SVHC (2014 Edition) of EU Reach.

[Typical Formulation]

•	White printing	Color printing
Ryudye [®] -W Colors	- -	0-5
Ryudye [®] -W KN White EFW-T	100-80	30-15
Ryudye [®] -W KN Clear EFC-T	0-20	70-80
Ryudye [®] -W Fixer	X	Χ
Total (Weight %)	100+X	100+X

[Printing Process]

Printing → Blow-drying or hot-drying (70-100 °C, 1Mins) → Heat Treatment (130-150 °C, 1-3Mins)

[Fastness Test]

Washing fastness test (60 °C×1Hr × 4times) : 4.0 - 5.0 Grade
Rubbing fastness test (JIS L-0849, 100Rounds / 3Mins) : 3.0 Grade
Note: Fastness Grade from 1.0 to 5.0, Grade 5.0 is the best.

[Matters Needing Attention]

- 1. In order to ensure excellent fatness, we advise adding the right amount of crosslinking agent Ryudye®-W Fixer J-52 (Long-time limiting, 24Hrs, 1.0-3.0%) or Ryudye®-W Fixer C (Short-time limiting, 8Hrs, 0.3-0.5%);
- 2. Adequate heat treatment can decrease stickiness of the printing surface and enhance the fastness:
- 3. Recommended screen mesh from 800 to 1,200;
- 4. In order to prevent drying too quickly and cause block up the screen when the humidity is too low (e.g. Autumn or Winter), you can add 1-3% wetting agent (Ryudye[®]-W Assister 502);
- 5. All matters in this instructions is obtained based on the standard test method, so in order to avoid any difference, the user must test according to their own use method and requirements before the product used for production.